



TECHNICAL DATA SHEET

PRODUCT

PROCOL XLS

Date : 07/09/06

Page 1
Version 3

1. PROPERTIES :

PROCOL XLS is a photopolymer emulsion of high viscosity . Solids content : 51%. Purple (sensitized brown colour) .
Shelf life : 1 year at 20°C in a dark room. Sensitized : 3 months at 20°C in a dark room.

2. PRINTING APPLICATION :

Resisting to all kinds of inks (water based inks, uv inks, uv water inks, solvents) including aggressive pastes. Excellent definition. It is very flexible and it resists to high pressure of the squeegee edges. One of the top range of emulsions, recommended for any work requiring a very high resolution and a very good mechanical resistance.

3. SENSITIZING :

Prepare the sensitizer by half filling the bottle with water. Dissolve the powder by shaking the bottle for at least one minute. Mix the sensitizer into the emulsion with a non-metallic instrument. Leave the sensitized emulsion to stand at least one hour to eliminate air bubbles.

COATING : Because of its high solids content, this emulsion can be used in one coat.

EXPOSURE TIME:

A preliminary test can be done using the following guidelines :

Use of a 3000 W lamp at 90 cm, 1 coat + 1 coat

Mesh :	Time (seconds):	Mesh :	Time (seconds) :
54 T White	174	120 T white	156
90 T White	162	140 T white	144

4. PERSONAL PROTECTION :

Inhalation :	None.
Eye contact :	Rinse immediately with plenty of water, also under the eyed lids, for at least 15 minutes. In the event of persistent irritation or any lesions , consult an oculist..
Skin contact :	Wash off with soap and water.
Ingestion :	Clean mouth with water .Do not induce vomiting.

5. SUPPLIED IN :



BOTTLE OF 0,9 KG



BOTTLE OF 4,5 KG